



Cosmic Plastics Inc
HELPING MOLD THE FUTURE



Registered To ISO 9001:2008
Ref. No. 10000711

TECHNICAL DATA SHEET

K61 / 6230 DAIP

DESCRIPTION Cosmic K61 / 6230 is a long-glass fiber filled, general purpose diallyl iso-phthalate molding compound which is supplied in a flake form. It can be preformed, and molds easily in standard compression, transfer equipment.

FEATURES K61 / 6230 has excellent mechanical and electrical properties with high dielectric strength and low dielectric constant. It has superior heat resistance and excellent machining qualities. K61 / 6230 has a shelf life of two years at room temperature with no reduction in performance.

APPLICATIONS The high strength of this material makes is ideal for switches, terminals, housings, cups, cases and insulators.

MATERIAL INFORMATION & PROPERTIES

MOLDING INFORMATION	SPECIFICATION	DATA
Specific Gravity		1.72
Bulk Factor		6.0
Molding Pressure	psi	500 – 8,000
Molding Temperature	°C	135 - 170
Mold Shrinkage	in / in	.001 - .004

MOISTURE PROPERTIES	SPECIFICATION	DATA
Water Absorption, %	48 hrs @ 50 °C	0.25

MECHANICAL PROPERTIES	SPECIFICATION	DATA
Impact Strength	Izod notched, ft-lb/inch	3.0 – 6.0
Flexural Strength	psi	13 – 17,000
Compressive Strength	psi	24 – 30,000
Tensile Strength	psi	6,000 – 10,000

THERMAL PROPERTIES	SPECIFICATION	DATA
Thermal Expansion, (-40 °C to 100 °C)	10 ⁻⁵ / °C	2.4
Heat Distortion Temp, (°C)	18.6 kg/cm ²	260
Dimensional Stability	% Max.	0.01

ELECTRICAL PROPERTIES	SPECIFICATION	DATA
Arc Resistance	seconds	180
Dielectric Strength, (Kv step-by-step)	volts/mil (Dry) volts/mil (Wet)	410 400
Dielectric Breakdown	Kv step-by-step (Dry) Kv step-by-step (Wet)	64 60
Dielectric Constant	1 KHz / 1 MHz (Dry) 1 KHz / 1 MHz (Wet)	4.0 / 3.8 4.1 / 3.9
Dissipation Factor	1 KHz / 1 MHz (Dry) 1 KHz / 1 MHz (Wet)	.008 / .012 .009 / .013
Volume Resistance, megaohms	As is 30 days @ 100% RH @70 °C	>10 ¹⁰ 6,000
Surface Resistance, megaohms	As is 30 days @ 100% RH @70 °C	>10 ¹⁰ 10 ⁴

CERTIFICATIONS	SPECIFICATION	DATA
ASTM D-5948-05; (MIL-M-14)	Type	GII-30 GDI-30
Flammability	None	N/A

Technical Data Sheets are offered For Reference Only, and are not to be considered as specifications. All tests were performed at room temperature (22 °C) unless otherwise stated, under carefully controlled conditions using transfer molded specimens. Since actual performance is determined by the molding techniques applied, as well as part size and shape, it is recommended that customers conduct their own tests to determine product suitability for their specific application. **Cosmic Plastics, Inc. makes no warranties of merchantability, or any expressed or implied guarantee or representation of fitness or suitability for any application.**

Approved: SC, 2/23/17

Copyright © 2017 Cosmic Plastics Inc. All Rights Reserved.

28410 Industry Dr.
Valencia, CA 91355

(661) 257-3274, (800) 423-5613, FAX (661) 257-3345
www.cosmicplastics.com

Eff: 2/23/17
TD-K61, Rev 0